



TECHNICAL INFORMATION

KALEX® 25134 Urethane Filter and Permeator Bonding Adhesive System

PRODUCT DESCRIPTION

KALEX 25134 is a two-component, fast setting, room temperature cure polyurethane system. This system designed for various end-cap forming and casting applications. It is semi-flexible and has a very low viscosity.

APPLICATION

KALEX 25134 is designed as an adhesive and casting resin for the filter industry. It can eliminate the need for separate end caps acting as both adhesive and casting end cap. It also acts as a soft casting resin for low volume prototype part production.

MIXING AND CURING SCHEDULE

The production of the desired polyurethane requires accurate measurement of the two components and adequate mixing. In general, hand-mixing small production runs is easily accomplished by weighing the two components. Machine mixing utilizes the volumetric ratio. Most machines are calibrated by weighing the components and adjusting the volume ratio. Larger volume hand mixing is easily controlled by filling pre-measured buckets to the indicated heights. The mix ratios are shown below.

	<u>Part A</u>	<u>Part B</u>
By weight	30	100
By volume	29	100

The cure schedule is dependent upon the temperature. The recommended cure schedule will vary with the desired properties. The recommended schedule to achieve the typical properties is shown below:

24 hours @ 25°C (77°F)

TYPICAL UNCURED PROPERTIES

	<u>Part A</u>	<u>Part B</u>	<u>Mixed</u>
Color	Dk. Amber	White	White
Viscosity @ 25°C, cps	60	1,800	1,500
Weight per Gallon, lbs.	10.2	9.7	9.8
Specific Gravity @ 25°C	1.22	1.16	1.18
Gel Time, minutes 25 gm mass @ 25°C	-----	-----	3
Filler Type	None	Non- Abrasive	Non- Abrasive
Shelf Life (in separate sealed containers), months	6	6	-----

TYPICAL CURED PROPERTIES

(Tested at 25°C unless otherwise indicated)

<u>Test</u>	<u>Result</u>
Hardness, Shore A	70

STORAGE AND HANDLING

These materials should be stored in a dry environment within a moderate temperature range. Extended exposure to temperatures above 35°C begins to degrade the Part A. Avoid exposing either component to moisture.

Moisture reacts with the A-side to create minor levels of by products. Low levels will not degrade the final polyurethane. Moisture contamination of the B-side will cause some gas bubbles in the mixed adhesive. Purge the container with dry air before closing to maintain the storage life.

When using meter-mixed dispense equipment (MMD) machines, reservoir should be blanketed with nitrogen or dry air to avoid moisture and other contamination.

Avoid contamination with oxidized metals (such as copper, brass, or mild steel), and rust or other metal oxides. The stability of the product is greatly reduced by materials such as strong acids or bases, sulfur compounds, amines, or reducing agents of any type.

SAFETY

These materials are intended for industrial use only and the practices of good housekeeping, safety and cleanliness should be followed before, during and after use.

Although the system contains low volatility materials, care should be taken in handling. Use adequate ventilation in the work area.

These materials may cause dermatitis in susceptible individuals. Keep off skin and out of eyes. In case of accidental skin contact, wash thoroughly with soap and water. In case of eye contact, flush eyes thoroughly with water and consult a physician immediately.

Refer to Materials Safety Data Sheet for additional information.

ADDITIONAL INFORMATION

Visit our web site at:
www.royaladhesives.com

Contact us at:
Royal Adhesives and Sealants, LLC

600 Cortlandt Street
Belleville, NJ 07109-3384
(888) 442-7362 Toll-free
(973) 751-3000 Phone
(973) 751-8407 Fax

NOTE

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement, which will not incorporate this document.